



Carbon nanotube reinforced hybrid composites: Computational modeling of environmental fatigue and usability for wind blades

Gaoming Dai*, Leon Mishnaevsky Jr.*

Department of Wind Energy, Technical University of Denmark, Roskilde, Denmark



ARTICLE INFO

Article history:

Received 23 January 2015

Received in revised form

6 February 2015

Accepted 10 March 2015

Available online 2 April 2015

Keywords:

A. Nano composites

A. Carbon nanotubes

B. Fatigue

C. Finite element analysis (FEA)

ABSTRACT

The potential of advanced carbon/glass hybrid reinforced composites with secondary carbon nanotube reinforcement for wind energy applications is investigated here with the use of computational experiments. Fatigue behavior of hybrid as well as glass and carbon fiber reinforced composites with and without secondary CNT reinforcement is simulated using multiscale 3D unit cells. The materials behavior under both mechanical cyclic loading and combined mechanical and environmental loading (with phase properties degraded due to the moisture effects) is studied. The multiscale unit cells are generated automatically using the Python based code. 3D computational studies of environment and fatigue analyses of multiscale composites with secondary nano-scale reinforcement in different material phases and different CNTs arrangements are carried out systematically in this paper. It was demonstrated that composites with the secondary CNT reinforcements (especially, aligned tubes) present superior fatigue performances than those without reinforcements, also under combined environmental and cyclic mechanical loading. This effect is stronger for carbon composites, than for hybrid and glass composites.

© 2015 Elsevier Ltd. All rights reserved.

1. Introduction

The future perspectives of wind energy utilization depend on the development and reliability of extra-large off-shore wind turbines [1]. Wind turbines are subject to long term cyclic mechanical and environmental loading, involving complex off-axis tensile, compressive and shear loading. The creation of such wind turbines requires the development of new, strong, fatigue resistant materials, which can sustain cyclic, random mechanical, thermal and environmental loadings over years keeping their high stiffness and integrity.

A number of experimental and computational studies have been carried out to develop better materials for wind turbines [1–7]. Among various ideas to enhance the performances of the composite materials for wind energy applications, two approaches attract a growing interest of research community and industry: hybrid composites and nanoreinforced composites.

Hybrid composites (e.g., mixed carbon and glass fibers) allow to combine the advantages of both groups of fibers (for the case of carbon/glass composites, low price of glass fibers, low weight and

high tensile strength and stiffness of carbon fibers) and compensate their weaknesses (again, high costs and low compressive strength of carbon fibers) [4–17]. So, Ong and Tsai [4] demonstrated that the full replacement of cheap and easily available glass fibers by very stiff, strong and lightweight carbon fibers for an 8 m wind turbine blades leads to 80% weight savings, and cost increase by 150%, while a partial (30%) replacement would lead to only 90% cost increase and 50% weight reduction. In a number of works, the strength and damage mechanisms of hybrid composites were studied. It was reported, among others, that the incorporation of glass fibers in carbon fiber reinforced composites allows the improvement of their impact properties and tensile strain to failure of the composite. Manders and Bader [11] observed an enhancement of the failure strain of the carbon fiber reinforced phase when “carbon fiber is combined with less-stiff higher-elongation glass fiber in a hybrid composite”.

Another approach to improve the composite performances (additionally to and keeping in place the advantages of both strong fibers and polymer matrix) is nanoreinforcing the matrix. It has been observed in many studies that the addition of small amount of nanoparticles (e.g. graphene, carbon nanotubes, or silicates and clay particles with high aspect ratios) to fiber reinforced composites can be used to improve composite properties [18–29]. According to Ref. [18], matrix-dominated properties (flexural and interlaminar

* Corresponding authors.

E-mail address: lemi@dtu.dk (L. Mishnaevsky Jr.).

shear strength) are drastically improved by the CNT additions to fiber-reinforced thermoplastic composites, while fiber-controlled properties (such as tensile strength and stiffness) are improved only slightly. In Refs. [19–21], the authors compared the composites with CNTs dispersed in matrix and distributed in fiber sizing. They observed that the crack initiation toughness increases (by 10% if CNTs in sizing and by 25% if in matrix) and the crack propagation toughness decreases (by 30–50%) when CNTs are placed in sizing [20]. However, in the system with carbon fibers, both crack initiation and propagation energies were improved by CNT addition in matrix [21], what is related with CNT bridging and other toughening mechanisms (crack deflection, blocking). In Ref. [22], it was shown that the tensile strength of glass fibers increases significantly with increasing CNT content. 45% increase in shear strength is achieved by adding 0.015 wt% nanotubes into glass fiber reinforced vinyl ester composite [23]. 30% enhancement of the inter-laminar shear strength was achieved by deposition of multi and single walled CNT on woven carbon fabric fibers in epoxy matrix [26,27]. Interlaminar toughness and strength of alumina fiber reinforced plastic laminates were improved by 76% and 9% due to the radially aligned CNTs in both inter-laminar and intra-laminar regions [28]. Thus, the secondary nanoreinforcement (e.g., carbon nanotubes or nanoclay distributed in polymer matrix or fiber sizing) have positive effect on the shear and compressive strength, fracture toughness and fatigue resistance of composites.

However, the question arises whether and to which degree this potential of material improvement is useful and usable for wind turbine blades, i.e. structures to be used under conditions of combined mechanical and environmental loading, high humidity, off-axis, complex loadings. A series of computational studies is carried out here in order to clarify the potential of these material modifications for wind blade materials. Using the numerical experiments, we seek to investigate how and whether the effects of hybrid and nanoreinforced structures of polymer composites (both each of them and combined) are beneficial for the fatigue resistance and service properties of the composites to be used in the wind turbine conditions. To do this, we use the computational micro-mechanics approach, based on multiscale and multi-element unit cell models [8,29], developed and tested in Ref. [29]. Collecting the literature data on the local materials properties and humidity effect on the properties of different phases, we introduce these data into the 3D multiscale computational models of composites and evaluate and compare the output materials performances. Carrying out computational experiments (numerical testing) of various composite structures, we explore the structure–mechanical properties relationships and can develop recommendations toward the improvement of the materials properties.

2. Computational model: generation, simulation, material properties

2.1. 3D hierarchical computational model: Python based model generation

Due to the large difference of the dimension scale of the fiber reinforced composite (macro-scale) and CNTs reinforcement (nano-scale), we use here the concept of macro-micro multiple-step modeling [29], to simulate the damage evolution in the material.

In order to carry our systematic computational studies of the microstructure–strength relationships of hybrid composites with secondary CNT reinforcements, a number of 3D computational models reflecting the hybrid composite structures should be generated. For this, a special Python based software code for the automatic generation of unit cells with multiple cylinder-like reinforcements [29–34] was generalized and improved. The newly

developed code allows to generate hierarchical FE models with pre-defined structures, including the macro-scale unit cell (with hybrid unidirectional/misaligned fibers and variable fiber content) and lower scale unit cell model (with aligned/random oriented carbon nanotubes, surrounded by the effective interface layers, see Refs. [37,38]), automatically. Examples of the models are shown in Fig. 1a. For comparison, we show a micrograph of a carbon fiber with CNTs, reprinted from Ref. [39] (Fig. 1b).

2.2. Micro-scale unit cell generation with multiple high aspect ratio CNTs: algorithm of cylinder distribution

For the generation of lower scale unit cell models with many high aspect ratio carbon nanotubes, the following approach has been used. The carbon nanotubes were presented as cylinders. The reinforcing CNTs are randomly distributed in the fiber–matrix interface and (in some models) randomly oriented. To take into account the interface effect, the generalized effective interface layer concept was used [30–38].

In order to distribute the high aspect ratio CNT cylinders in the microscope unit cell, the following algorithm was used. The condition that the CNTs do not overlap is written as follows:

$$\begin{aligned} d_{f-f} &\geq 2R_f \\ d_{CNT-CNT} &\geq 2r_{CNT} \\ d_{f-CNT} &\geq R_f + r_{CNT} \end{aligned} \quad (1)$$

where, d_{f-f} , $d_{CNT-CNT}$, d_{f-CNT} are distances between closest fibers, closest CNTs and a fiber and CNT, respectively, R_f – radius of fiber, r_{CNT} – radius of carbon nanotube. When generating the unit cell with multiple randomly oriented CNTs, the program places each new CNT into the cell one after another, using random number generator to get the new CNT location and checking that the reinforcements don't overlap. For this, the distance between straight lines (CNT cylinder axes) located in different planes was calculated using the spatial vector projection theory. We take $P_1(x_1, y_1, z_1)$ and $P_2(x_2, y_2, z_2)$ as two points on the central line of new CNT cylinder (the line is marked as L_1) and $P_3(x_3, y_3, z_3)$ and $P_4(x_4, y_4, z_4)$ as two points on the central line of one of the existing CNT cylinders (marked as L_2). From the analytic geometry, the direction vector of l_1 and l_2 are described as

$$\begin{aligned} \vec{L}_1 &= (x_2 - x_1, y_2 - y_1, z_2 - z_1) \\ \vec{L}_2 &= (x_4 - x_3, y_4 - y_3, z_4 - z_3) \end{aligned} \quad (2)$$

The vector of common perpendicular (marked as l) of the two lines is given by:


$$\vec{l} = \vec{L}_1 \times \vec{L}_2 = \begin{vmatrix} i & j & k \\ x_2 - x_1 & y_2 - y_1 & z_2 - z_1 \\ x_4 - x_3 & y_4 - y_3 & z_4 - z_3 \end{vmatrix} \quad (3)$$

After some simplifications

$$\begin{aligned} \vec{l} &= \vec{L}_1 \times \vec{L}_2 \\ &= \left((y_2 - y_1) \cdot (z_4 - z_3) - (y_4 - y_3) \cdot (z_2 - z_1), \right. \\ &\quad \left. (z_2 - z_1) \cdot (x_4 - x_3) - (z_4 - z_3) \cdot (x_2 - x_1), \right. \\ &\quad \left. (x_2 - x_1) \cdot (y_4 - y_3) - (x_4 - x_3) \cdot (y_2 - y_1) \right) \\ &= (E, F, G) \end{aligned} \quad (4)$$

Taking arbitrary points (P_1 and P_3 as examples) on L_1 and L_2 , we consider the projection of line P_1P_3 on the common perpendicular, which in fact represents the distance between the two lines.

The direction vector of line P_1P_3 can be described as



GFRC: glass fiber reinforced composite HC: hybrid composite CFRC: carbon fiber reinforced composite
EI: effective interface

a

Fig. 1. Schema of the multiscale model, (a) and a micrograph of a carbon fiber with CNT reinforcements in fiber–matrix interface.
Reprinted from Ref. [39] with kind permission from Elsevier.

$$\overrightarrow{P_1 P_3} = (x_3 - x_1, y_3 - y_1, z_3 - z_1) \quad (5)$$

and the distance between the lines (axes of CNTs) is then given as

$$d = \left| \operatorname{Prj}_{\vec{L}} \overrightarrow{P_1 P_3} \right| \quad (6)$$

$$= \frac{\vec{L} \cdot \overrightarrow{P_1 P_3}}{|\vec{L}|} = \frac{E \cdot (x_3 - x_1) + F \cdot (y_3 - y_1) + G \cdot (z_3 - z_1)}{\sqrt{E^2 + F^2 + G^2}}$$

The distance d between any two misaligned lines can be calculated based on these equations. The distance can be

$$d = \sqrt{(x_1 - x_2)^2 + (y_1 - y_2)^2} \quad (7)$$

The value d obtained from Eqs. (6) and (7) is introduced into Eq. (1). If at least one condition is not fulfilled, the possible new place for the CNT is generated again, and a new test is started.

2.3. Modeling of material fatigue and moisture effect

The 3D models were subjected to the uniaxial periodic cyclic compressive loading (displacement) u along the Z-axis direction (the same values but opposite directions on both upper and lower faces of the box). All the simulations were carried out using ABAQUS/STANDARD finite element program (version 6.11). The three-dimensional 8-node linear brick finite element with reduced integration element C3D8R were used in the global scale analysis, and three-dimensional 4-node linear tetrahedron element C3D4 were used in the submodel analysis.

In order to simulate the fatigue damage evolution, two step procedure was employed [10,29]. Initial defects (with the sizes of the order of one–two finite elements) were introduced into the macro-scale model by subjecting the unit cell to a quasi-static load before the cyclic loading. After the initial defects are formed, the fatigue modeling for macro-scale model is carried out. Both the crack growth onset and crack propagation are described using the

Paris law: $da/dN = c_1(\Delta G)^{c_2}$, where da/dN is the crack growth rate (fatigue crack length growth per loading cycle), c_1 and c_2 are material constants while ΔG represents the range of strain energy release rate, for example, the difference between the strain energy release rate at the peak and valley loading. The crack propagation analysis is carried out in the framework of the linear elastic fracture mechanics (LEFM) approach and is based on the extended-FEM method [40]. The Virtual Crack Closure Technique (VCCT) [41–43] is employed to calculate the strain energy release rate at the crack tip.

The degradation of wind turbine materials under real conditions is controlled by both mechanical and environmental loadings. The time scales of the fatigue degradation and the moisture distribution in the composite body differ drastically: while the fatigue degradation might extend over several dozens of years, the moisture is distributed over the material during minutes till hours.

That is why, as a first approximation, we neglect the time-dependency of the moisture-controlled degradation of phase properties. Instead, we assume the permanently reduced phase properties (due to the moisture effect) when simulating the material behavior of the materials under environmental loading. The degrees of reduction of the phase properties are different for fibers, interfaces, polymer, and are determined from experimental/literature data. These degrees are determined from reviewing literature data. The overview of the data on the material properties degradation is given in the Section 2.5.

2.4. Material properties in dry state

Below, the mechanical properties of the main phases (glass and carbon fibers, epoxy, CNT, interphases/interfaces) used in the simulations are presented. Most data are taken from literature, also from earlier works of the authors [10,29,34] (both because these data are relatively well justified and to ensure the comparability of results).

Polymer (epoxy) matrix: Young's modulus of 1.9 GPa, Poisson's ratio of 0.37; tensile strength of 68 MPa, compression strength of 88 MPa [10].

Carbon fiber: Young's modulus 276 GPa, Poisson's ratio is 0.37 [35]; tensile and compressive strengths are 3000 MPa and 2800 MPa, respectively [10]. Radius of carbon fiber is 4 μm .

Glass fibers: Radius 8 μm , Young's modulus is 72 GPa, Poisson's ratio is 0.26; tensile and compressive strengths are 2500 MPa and 1500 MPa, respectively [29,36].

Carbon nanotubes (CNT): The Young's modulus of SWCNT was taken 1 TPa and the Poisson ratio is 0.2 [44]. The tensile strength is taken as 30 GPa [45,46]. The radius of carbon nanotube is 0.01 nm while the length of the CNT is 0.8 μm .

CNT/matrix interface: Young modulus of CNT–matrix interface is taken here as 3.74 GPa, following the inverse analysis of graphene–epoxy interface [34].

The interface thicknesses of both glass fiber–matrix interface and carbon fiber–matrix interface were taken as 1.0 μm (slightly larger than the CNT length of 0.8 μm). According to Refs. [47,48], the soft interface layer can be assigned the elastic modulus of $E_i = (E_{\text{CNT}} + E_{\text{matrix}})/20$ while the stiff interface layer can be assigned a higher Young's modulus as $E_i = (E_{\text{CNT}} + E_{\text{matrix}})/2$. The interface stiffness can vary therefore in the range from soft to stiff, with the ratio E_i/E_{matrix} from 0.55 to 5.5. Thus, taking the interface layer stiffness as an average value, between "soft" and "stiff" ones, we have the elastic modulus of the fiber–matrix interface as $E_i = (E_{\text{fiber}} + E_{\text{matrix}})/10$. Then we get: Carbon/matrix interface: the Young's modulus is $E_{\text{CM}} = (E_{\text{Carbonfiber}} + E_{\text{matrix}})/10 = 27.79$ GPa. Glass/matrix interface: The Young's modulus is $E_{\text{GM}} = (E_{\text{Glassfiber}} + E_{\text{matrix}})/10 = 7.39$ GPa. According to Ref. [49], the strength of the interfaces between the epoxy resin and glass fiber is around 0.57 of that between carbon and epoxy.

The fatigue behavior is modeled using the Paris's law $da/dN = c_1(\Delta G)^{c_2}$, where a – crack length, N – number of cycle. The threshold and critical strain energy release rates of different material phases and different fracture modes have been determined on the basis of literature data [50–59], inverse modeling and estimations. Using the estimation by Reeder [50] that "This is generic to any material with pure mode ratios of 3 and 6, (G_{IIc}/G_{Ic} and G_{IIIc}/G_{Ic} , respectively) which are reasonable values...", we could determine the $G_{II, IIIc}$ values from G_{Ic} .

For the strain energy release rate for fibers, we used the formulation by Pinho et al. [53]:

$$G_{Ic}|_{\text{fiber}} = 2G_{Ic}|_{\text{laminate}} - G_{Ic}|_{\text{matrix intra}} \quad (8)$$

here, $G_{Ic}|_{\text{fiber}}$, $G_{Ic}|_{\text{laminate}}$ and $G_{Ic}|_{\text{matrix}}$ stands for the critical strain energy release rate for fiber, the fiber reinforced laminate and the matrix, respectively. Other data are listed below, with references:

- Matrix: $G_{Ith} = 0.06$ kJ/m² [54], $G_{Ic} = 0.17$ kJ/m² [54], $G_{IIth} = 0.24$ kJ/m², $G_{IIc} = 0.49$ kJ/m² [54], $G_{IIIth} = 0.306$ kJ/m², $G_{IIIc} = 0.49$ kJ/m² [54].
- Glass fiber: $G_{Ith} = 0.068$ kJ/m² (Eq. (8) and [55]), $G_{Ic} = 0.288$ kJ/m² (Eq. (8) and [55]), $G_{IIth} = 0.59$ kJ/m² (Eq. (8) and [55]), $G_{IIc} = 1.53$ kJ/m² (Eq. (8) and [55]), $G_{IIIth} = 0.994$ kJ/m² (Eq. (8) and [51]), $G_{IIIc} = 1.21$ kJ/m² (Eq. (8) and [51]).
- Carbon fibers: $G_{Ith} = 0.098$ kJ/m² (Eq. (8) and [57]), $G_{Ic} = 0.636$ kJ/m² (Eq. (8) and [56]), $G_{IIth} = 0.712$ kJ/m² (Eq. (8) and [58]), $G_{IIc} = 3.744$ kJ/m² (Eq. (8) and [58]), $G_{IIIth} = 1.598$ kJ/m², $G_{IIIc} = 7.978$ kJ/m².
- Glass–matrix interface: $G_{Ith} = 0.064$ kJ/m² [55], $G_{Ic} = 0.229$ kJ/m² [55], $G_{IIth} = 0.415$ kJ/m² [55], $G_{IIc} = 1.01$ kJ/m² [55], $G_{IIIth} = 0.650$ kJ/m² [51], $G_{IIIc} = 0.850$ kJ/m² [51].
- Carbon–matrix interface: $G_{Ith} = 0.079$ kJ/m² [57], $G_{Ic} = 0.403$ kJ/m² [56], $G_{IIth} = 0.476$ kJ/m² [58], $G_{IIc} = 2.117$ kJ/m² [58], $G_{IIIth} = 0.952$ kJ/m², $G_{IIIc} = 4.234$ kJ/m².

Finally, two material constants c_1, c_2 from Ref. [40] were used: $c_1 = 2.44 \times 10^6$ and $c_2 = 10.61$.

2.5. Changing material properties under environmental (moisture) loading: overview of literature and data collection

In order to evaluate the effect of environmental loading on the lifetime of various composites, we carried out an overview of literature data on the humidity effect on the mechanical properties and strength of the phases.

Due to the expected off-shore location of the large wind turbines, we consider the effect of seawater on the phase properties. The relative humidity in air is taken as 60% [60].

Below, an overview of literature data and available estimations of the stiffness and strength reduction due to the humidity under given conditions are presented. These data are included in our simulations as input data.

As noted in Refs. [61,62], moisture absorption causes plasticization and swelling of epoxy matrix, and that weakens the interfacial strength between epoxy and reinforcements, degradation of crosslinks and segments rigidity. Let us consider all the main phases in the materials and the dependences of their properties on the long term high humidity:

Polymer (epoxy) matrix: Zafar et al. [63] observed that Young modulus of epoxy is reduced by 5% and tensile strength is reduced by 15–18% due to moisture. As observed by Mei Li [64], epoxy matrix can absorb up to 2.2% moisture (Chawla [65] however noticed that matrices can absorb only up to 1% of weight).

Carbon fiber: According to Ref. [65], "the carbon fiber itself is unaffected by moisture", so the Young's modulus of carbon fiber under moisture condition will be the same as the dry condition. According to Ref. [63], the maximum applied stress before the fiber fracture is reduced in seawater by 1.33 times (after 60 h)–2 times (after 230 h). The G_{Ic} remains almost constant as a result of moisture [49], while G_{IIc} is reduced drastically, 2.04 times. According to Ref. [66], carbon fiber has the $G_{Ic} = 0.860$ kJ/m² and $G_{IIc} = 3.076$ kJ/m², respectively under humidity condition.

Glass fibers: As noted by Li [64], the tensile strength of glass fibers can be reduced up to 20% if the moisture content is above 1%. In Guedes et al.'s work [67], they present that the critical strain energy release rate in model I, G_{Ic} , show a decrease between 5% and 10% when conditioned in water. According to Ref. [66], glass fiber has the $G_{Ic} = 2.152$ kJ/m² and $G_{IIc} = 4.668$ kJ/m², respectively under humidity condition.

Carbon nanotubes (CNT): CNT properties are not changed under changing humidity conditions.

Carbon/matrix interface: According to Ref. [63], the maximum applied stress before the interfacial failure is reduced by 1.9 times after 60 h in seawater. van der Wal [68], referring to Ray [49] noticed that epoxy carbon interface is reduced by 10% at high temperature under the humidity effect. Considering the interface as a three layer multilayer [69] (fiber/sizing interface with covalent chemical bonding; an interphase of oligomers with increasing crosslink density towards the fiber/sizing interface and the sizing/epoxy interface with covalent chemical bonding), van der Wal [68] noted that reaction with water and the formation of the microscopic solution can take place probably in oligomer phase. Grant and Bradley [70] studied the degradation of graphite/epoxy composites due to seawater immersion. Through observation by scanning electron microscopy (SEM), they found out that the measured 17% decrease in transverse tension strength was associated with the degradation of the interface.

CNT/matrix interface: According to Ref. [61], tensile strength of unmodified CNT/epoxy composite is 16% lower in seawater state than in dry state; Young modulus is 5% lower, fracture load and toughness-66% lower, K_{IC} -40% lower. In Ref. [61], the fracture surface (of unmodified CNT/epoxy) showed brittle fracture in dry state and “delaminated epoxy matrix due to tear down” in humid composite. Jen and Huang [71], however, studied fracture surface on CNT/epoxy nanocomposites, and did not observe the visible increase in the length of pulled out CNTS due to the moisture effect (but did observe it due to the combined moisture and high temperature effects).

Glass/matrix interface: According to the experiments by Ray [49], the ILSS (interlaminar shear stress) of both carbon and glass/epoxy interfaces are reduced by 1.5 times (while it is 120 for carbon and 27 for glass in dry conditions; the same numbers are mentioned in Ref. [68], around 100 and 27 MPa). The authors of Ref. [66] noted that the mode I interlaminar fracture toughness decreases “upon water absorption for the glass fiber laminates, while the carbon fiber materials showed an increase in G_{IC} under the same conditions. Mode II interlaminar fracture toughness as well as flexural modulus and flexural strength were observed to decrease upon water absorption, and to recover slightly after water desorption.” Also, Adams and Singh [72] observed that glass/polymer interfaces are much more severely degraded due to the moisture than the carbon/polymer interfaces.

The parameters c_1 and c_2 of Paris's law $da/dN = c_1(\Delta G)^{c_2}$ have been obtained as follows:

For the polymer matrix, the experimental data of the delamination growth rate versus the strain energy release rate of fracture toughness for an epoxy material from Ref. [73] were fitted into a power law function. From the fitting curves, the parameters c_1 and c_2 were determined: $c_1 = 3.2187 \times 10^{-8}$ and $c_2 = 8.776$. The material parameters for other phases (glass and carbon fibers and interfaces) were determined using the same fitting procedures. The curves for glass fiber and glass fiber–matrix interface were fitted using the data from Ref. [74]. The resulting values are: $c_1 = 11.07 \times 10^{-2}$ and $c_2 = 22$, for glass fibers. For glass fiber/matrix interfaces, the values are $c_1 = 12.1 \times 10^{-1.1}$ and $c_2 = 16.10$, respectively. The curves for carbon fiber and carbon fiber–matrix interface were determined using the inverse method presented in work [40] and the data given in Ref. [75]. The parameter values for the carbon fibers are: $c_1 = 7.4 \times 10^{-4.3}$ and $c_2 = 29.54$, respectively. The parameters for carbon fiber–matrix interface is $c_1 = 14.1 \times 10^{-1.8}$ and $c_2 = 19.73$, respectively.

The resulting values used in the following simulations (for dry case and a case of long term 60% seawater humidity effect) are given in Table 1.

3. Computational experiments: effect of environmental loading on fatigue lifetime

In this section, the effect of environmental loading, overlaying the cyclic mechanical loading, on the fatigue performances of hybrid and nanoreinforced composites is systematically studied in numerical experiments. Various microstructures of hybrid and hierarchical composites, with different fractions of carbon fibers, distribution and alignment of CNT are considered in the computational experiments. The generated unit cell models are subject to tension–compression cyclic loading with the stress ratio $R = -1$.

3.1. Hybrid composites: effect of carbon content on lifetime under combined environmental plus cyclic loading

Here, we seek to investigate the effect of the hybrid structure of UD composites (with carbon and glass fibers, and varied fractions of carbon versus glass) on the fatigue performance of composites under combined environmental/mechanical cyclic loading. Fig. 2a shows an example of unit cell FE models with 50% carbon fiber content.

Fig. 3a shows the calculated S–N curves for hybrid composites under pure mechanical cyclic loading (tension–compression) and under combined mechanical/environmental loading. All the data are normalized by the original maximum applied stress (311.65 MPa) of the 50/50% hybrid composite without environmental loading.

One can see that the composite with pure carbon fiber reinforcement shows the highest stress and longest life under the same while the composite with glass fiber reinforcement demonstrate the lowest stress and shortest lifetime.

The stress corresponding to a given cycles number (here 1.43×10^7 cycles) strongly depends on the moisture effect. While the high humidity environment leads to the 14.28% reduction of the stress for the given N for pure carbon fiber reinforced composites, it leads to 36.53% reduction for 50/50% hybrid composites and even 489.24% reduction for pure glass composites. For comparison, the differences in stresses for quasi-static/low cycle case (1–2 cycles) are much lower: 7.89% (carbon), 9.91% (50/50 hybrid) and 11.21% (pure glass).

The ratio between the stresses (corresponding to a given number of cycles) for different composites depends on the humidity as well.

Table 1
Effect of moisture on the local phase properties.

		Young, GPa	G_I , kJ/m ²	G_{II} , kJ/m ²	c_1	c_2
CNT		2550	—	—	—	—
Carbon fiber	Dry	276	0.919	4.995	2.76×10^{-8}	6.4
	Humid	276	0.860	3.076	$7.4 \times 10^{-4.3}$	29.54
Glass fiber	Dry	72	2.302	5.768	1.26×10^{-5}	4.53
	Humid	57.6	2.152	4.668	11.07×10^{-2}	22
Epoxy	Dry	1.9	0.173	0.648	2.8461×10^{-9}	-12.415
	Humid	1.805	0.173	0.324	3.2187×10^{-8}	8.776
IF CNT/E	Dry	3.74	0.447	1.93	4.253×10^{-6}	-8.121
	Humid	3.553	0.2682	1.1966	1.354×10^{-4}	14.21
IF C/E	Dry	27.79	0.379	1.70	2.125×10^{-7}	5.26
	Humid	19.125	0.252	1.13	6.148×10^{-3}	22.65
IF G/E	Dry	7.39	0.682	2.245	5.7623×10^{-7}	-9.542
	Humid	6.72	0.455	1.497	3.678×10^{-2}	14.321

(IF: interface; C/E: carbon fiber and epoxy; G/E: glass fiber and epoxy).




Fig. 2. Examples of multielement unit cells (a) 50/50 glass/carbon hybrid composite without CNT (b) with CNT reinforcement, (c) carbon reinforced composite with CNTs.

For the dry cyclic (low cycle) loading, this stress for carbon composite is 1.18 times higher than that for 50/50 hybrid composite and 1.51 times higher than that for pure glass. For the case of 1.43×10^7 cycles (dry loading), these ratios are 1.98 and 4.12.

This corresponds also to results of Shan and Liao [76] who noticed that “because carbon fibers are resistant to water and dilute acid, glass–carbon hybrid composites as a whole are more resistant to stress corrosion than all-glass fiber composites”. They




Fig. 3. S–N curves for hybrid composites under pure mechanical cyclic loading (tension–compression) under dry and long term high humidity conditions (a) without CNT reinforcement, and (b) with CNT reinforcement under dry and (c) with CNTs under humid conditions.

demonstrated experimentally that hybrid carbon/glass composites show much higher lifetime than pure glass composites under environmental plus mechanical cyclic loading, and observed 500% fatigue life difference for wet hybrid samples and wet pure glass samples [76,77]. Selzer and Friedrich [78] observed 7–15% reduction of fatigue lifetime for the carbon fiber reinforced composites under dry and high moisture conditions. These numbers correspond qualitatively to the above estimations.

3.2. CNT reinforced composites: effect of secondary CNT reinforcement on fatigue resistance under cyclic loading

In this section, we investigate the effect of secondary CNT reinforcement on the fatigue performance of composites under mechanical tension–compression cyclic loading.

Fig. 2b, c shows some examples of macro-micro FE unit cell models of composites with CNT reinforcements. The CNT reinforcement is localized in the fiber/matrix sizing (interface layer). The volume content is 0.05%.

Fig. 3b shows the calculated S–N curves for hybrid composites with/without CNT reinforcements under pure mechanical cyclic loading (tension–compression) and under combined mechanical/environmental loading. One can see that the CNT enhances the fatigue performance (maximum stress and lifetime) in all considered composites.

Again, considering the stress corresponding to a given cycles number (again, 1.72×10^7 cycles), we can see that the effect of CNT reinforcement strongly depends on the kind of loading. While CNT reinforcement always increases the fatigue resistance, it works differently for very low cycle loading and high cycle loading. For the very low cycle loading, the CNT reinforcement leads to 25–43% increase in the stress, while for the millions of cycles, the CNT effect increases the stress by 64–120%. It is of interest also that while for quasi-static/low cycle loading, the strongest effect is observed for carbon composites (43%, versus 25% for pure glass and 32% for hybrids), the strongest effect of high cycle loading is observed for glass fiber composite (120%, versus 64% for pure carbon and 107% for hybrids).

The ratio between the stress (corresponding to a given number of cycles) for different composites slightly depend on the CNT reinforcement: this stress for carbon composites is (for high cycle fatigue) 43% (no CNT)–80% (with CNT) higher than that for 50/50 hybrids and 3.6 (no CNT)–4.8 (CNT) times higher than for glass composites.

Fig. 4 shows the crack interaction with the CNTs in the fiber/matrix interface. The damage mechanisms such as nanotube breaking, bridging and pull-out are observed. The same damage and toughening mechanisms were observed on the fatigue crack surfaces of CNT/polymer nanocomposites analyzed by Jen and Huang [79]. Knoll et al. [80] also observed 2–5 fold increase in the fatigue life of carbon fiber composites due to the MWCNT secondary reinforcement.

3.3. Environmental loading of hybrid composites with secondary CNT reinforcement

In this section, we investigate the effect of secondary CNT reinforcement on the fatigue performance of composites under combined environmental/mechanical cyclic loading.

Fig. 3c shows the S–N curves of 50/50 glass/carbon fiber reinforced hybrid composites with secondary CNT reinforcement under cyclic fatigue with high humidity. Considering the stress corresponding to a given cycles number (1.72×10^7 cycles), we can see that the effect of environmental (moisture) loading on the fatigue behavior of CNT reinforced composites in general follows the effect of moisture on the properties of hybrid composites without CNT reinforcement. One can see that the moisture effect on the CNT reinforced glass composites is weaker than on pure glass composites: the stress is only 3.5 times higher for mechanical high cycle loading and 35% higher for mechanical low cycle fatigue than for combined mechanical + environmental loading (compared with 5 times higher for non-CNT high cycle case) and 65% higher for low cycle case. For pure carbon composites, the CNT reinforcement doesn't have visible effect of the moisture resistance.

These results correspond to a number of experimental studies. So, Loos et al. [81] observed the increase of fatigue lifetime by 1550% in the high-cycle, low-stress amplitude regime due to the small additions of CNTs. The crack propagation rate in epoxy is reduced by an order of magnitude if 0.5 wt% CNTs is added [82]. The authors of Ref. [83] demonstrated that fatigue crack growth rates can be reduced up to 20-times by controlling CNT parameters, namely, choosing CNTs with smaller diameter, increasing the CNT length and improving its dispersion.

3.4. Effect of the orientation of secondary CNT reinforcement on the composite performances

In this section, the effect of the orientation of the secondary CNT reinforcements (aligned versus randomly oriented) on the fatigue behavior under high humidity conditions is considered. We consider 50/50 glass/fiber reinforced hybrid composites with various CNT secondary reinforcements (aligned along the fibers and randomly oriented).

Fig. 5 shows the results of the fatigue analysis (a) and the unit cell models of composite with CNT reinforcements (b). The stress values are normalized by the maximum applied stress of the aligned CNT reinforced hybrid composite without moisture effect (524.41 MPa). One can see that the composite with aligned CNTs in the sizing is much stronger than that with randomly oriented CNTs. The stress level of the composite with aligned CNTs, corresponding to low level cycle fatigue/static loading, is 17% higher than that with random CNTs (under dry conditions). The number increases to 22% under high humidity conditions.

The (mis)orientation of CNTs has a strong influence on the composite sensitivity to humidity as well: the low cycle fatigue




Fig. 4. Crack interaction with CNTs.




Fig. 5. S–N curves of the composites with different alignment of CNTs (a) and unit cell models with varied CNT alignment: (b) aligned (c) random.

stress is reduced by 4% as a result of high humidity if the CNTs are aligned, and by 9% if they are random oriented. The stress, corresponding to the long cycle loading (here, 1.43×10^7) stress is reduced by 26% as a result of high humidity if the CNTs are aligned, and by 31% if they are random oriented.

3.5. Effect of CNT distribution (fiber sizing vs. matrix) on the composite performances

In this subsection, we seek to study the effect of the CNT distribution/location on the fatigue resistance of the composites. The cases of hybrid composites with CNTs localized either in the fiber sizing or distributed in the matrix are considered. The total number of CNTs in the model (9.450×10^5) is fixed and the same in both cases. Apparently, the content of CNTs in the sizing is therefore much higher than in the matrix (0.02% is the model with

nanoreinforced sizing, and 0.005% in the model with CNTs in the matrix). They have been defined following the procedure described in Ref. [29]. All the CNTs are random arranged in either fiber sizing or matrix.

Fig. 6a shows S–N curves of hybrid composite with secondary CNT reinforcements in fiber sizing or in matrix, subject to the mechanical cycling loading with and without high humidity.

The examples of the unit cell models are shown in Fig. 6b, c. It is seen that the composite with CNT reinforcements in fiber sizing show the better fatigue performance than those with the CNT reinforcements in matrix, both in dry and high humidity conditions.

The stress level strongly depends on the location of the CNT reinforcements and the moisture effect, but these dependences are different for different composites. The high humidity leads to the 14.3% reduction of the stress for the given amount of cycles $N = 1.43 \times 10^7$ for hybrid composites with CNT reinforcements in




Fig. 6. S–N curves of hybrid composite with secondary CNT reinforcements in fiber sizing or in matrix (a) and examples of the models (b).

fiber sizing, and to even higher 25.5% reduction for hybrid composite with CNT reinforcements in matrix. For comparison, the differences in stresses for quasi-static/low cycle case (1–2 cycles) are much lower, which are 4.2% and 8.4% for the hybrid composite with CNT reinforcements in fiber sizing and matrix, respectively.

The conclusion that the CNT reinforcement in the fiber sizing increases drastically both the fatigue lifetime and the moisture sensitivity of the composites, much more efficiently than for the CNTs distributed in the matrix, corresponds also the observations from Ref. [84] about nanostructured interfaces as a best way to enhance the materials strength.

3.6. Effect of off-axis loading

While most material testing procedures are based on axial tensile or compression loading, the wind blade composites are subject to off-axis, often multiaxial, compression plus shear loading [85].

In his section, we seek to investigate the effect of the CNT reinforcement on the fatigue lifetime under off-axis cyclic loading, under dry and high humidity conditions. The angle between fibers and loading vectors in the off-axis model was 12%. The two models have the same fiber and CNTs volume fraction and loading condition.

Fig. 7 shows S–N curves of hybrid composite with and without secondary CNT reinforcements, subject to the axial and off-axis mechanical cycling loading with and without high humidity. As expected, the fatigue life is much lower under off-axis loading than under axial loading.

The stresses corresponding to low cycle loading and to the given cycle number, 1.43×10^7 , are 12.2% and 14.1% lower for the off-axis loading, respectively. For the case under high humidity conditions, these values are lower for the off-axis loading by 7.6 and 9.7% respectively.

Comparing the stresses corresponding to the low and high cycle numbers for non-CNT-reinforced and CNT reinforced hybrid composites and dry/humid cases, one can see that the stress is reduced by 30% in dry case (without CNT) due to the off-axis loading. In humid conditions, the stress is reduced much stronger: 45% for low

cycle/static and 6 times for high cycle loading. In the case with CNT, the stress is reduced by 13–23% in dry conditions, and by only 19–30% in humid conditions. This is an important conclusion: the CNT reinforcement allows to drastically reduce the fatigue life sensitivity to off-axis loading, also under high humidity conditions.

4. Applicability to wind turbine blade materials

In this section, we seek to evaluate the feasibility of using hybrid and nanoreinforced composites in wind blades, as a replacement for the currently used glass fiber/epoxy composites. As noted above, the reliability of wind turbine blades is determined in many cases by the matrix and sizing controlled properties, i.e. those which are controlled and influenced by the secondary nanoreinforcement. Thus, the nanoreinforced and hybrid composites have a great potential to be used in order to improve the wind blade materials performances.

The important requirement toward wind blade materials is their economic efficiency, i.e. the gains in strength and lifetime should overweight the additional costs. Let us make a rough estimation of the economic feasibility of new materials for wind energy applications.

The cost of energy over whole lifetime of the wind turbine can be estimated using the following formula [86]:

$$CoE_{total} = \frac{C * FCR + M}{P_{Avg} T} \quad (9)$$

where P_{Avg} – average power generation per hour, T – lifetime in hours, FCR – fixed charge rate (taken in Ref. [86] as 10%), M – maintenance costs (taken as 2% installed capital costs in Ref. [86]), C – capital investment for a turbine, which is calculated as [87]: $C = c P_{rat}$, P_{rat} – rated (maximum) turbine power, c – coefficient, $c = 1100 \text{ €/kW}$ (land based) or $1500\text{--}2000 \text{ €/kW}$ (off-shore turbine). The average power generation P_{Avg} is calculated as [87]:

$P_{Avg} = \int_{U_{in}}^{U_{out}} P(U)f(U)dU$, where U – undisturbed wind speed, $f(U)$ – wind speed probability density given by Weibull distribution with shape factor 2, U_{in} and U_{out} – start and stop wind speeds of the




Fig. 7. S–N curves of the composites with CNT reinforcement axial loading and off-axis loading (a) and schemas of unit cell models and loading (b).

wind turbine, $P(U)$ – power at the wind speed U , $P(U)$ can be calculated as $C_p \rho A U^3 / 2$, C_p – power coefficient (≤ 0.59), ρ – air density, A – rotor swept area, $A = \pi R^2$, R – turbine radius. C_p can be taken 0.45 [87]. Simplifying, we have: $P_{Avg} = 0.23\pi R^2 C_p$, where

$$C_p = \int_{U_{in}}^{U_{out}} \rho U^3 f(U) dU.$$

Let's assume that the cost of a wind turbine is increased by C_{nano} times, as a result of using nanoengineered materials. From the formula (9), one can see that if additional costs for the fabrication of a blade from nanoengineered material lead to the increase of capital investments per turbine for instance by 20%, the expected increase of the lifetime of the turbine should be at least higher than that, to keep the costs of energy at the same level.

Veers and colleagues [88] derived a very simplified analytical equation linking the lifetime of a turbine component to the wind speed and materials fatigue properties:

$$T = \left[C f_0 \left(\frac{\sqrt{2} M K V_m}{(1 - S_m/S_u)(1/\alpha)!} \right)^b \left(\frac{b}{2} \right)! \left(\frac{b}{\alpha} \right)! \right]^{-1} \quad (10)$$

where C and b – coefficient and power coefficient of S–N curve of the material, $N = C \sigma^{-b}$, f_0 – average frequency, S_m , S_u are mean stress and ultimate strength of WT material, V_m – mean wind speed, α – parameter of Rayleigh law distribution for wind speed variation, K – stress concentration factor [89]. Collecting all the material-independent terms in a coefficient, we can rewrite equation (10) as: $T = C_{mi}(1 - S_m/S_u)^{-b}/C(MK)^b[(b/2)!(b/\alpha)!]^{-1}$. Designating the cost of energy for a basic case (glass fiber epoxy composites) as CoE_1 , and using equation (9), we can define the allowable upper limit for C_{nano} as a relative increase of the lifetime of blade from each material as compared with basic cases (here, glass fiber epoxy composite):

$$C_{nano}^{\max} < \frac{CoE_2}{CoE_1} = \frac{C_2(K_2)^{b_2}(1 - S_m/S_{u1})^{-b_1}}{C_1(K_1)^{b_1}(1 - S_m/S_{u2})^{-b_2}} \frac{\left(\frac{b_2}{2}\right)! \left(\frac{b_2}{\alpha}\right)!}{\left(\frac{b_1}{2}\right)! \left(\frac{b_1}{\alpha}\right)!} \quad (11)$$

where indices 1 and 2 refer to the basic case (here, glass fibers) and considered case of a composite with modified structure, respectively. These formulas are very approximate, but can give some qualitative estimations under which conditions the replacement of the traditional.

Let us estimate how the materials modifications considered above influence the turbine lifetime. Table 2 shows the coefficients b and C determined in our simulations above.

Substituting these values into the formula (11), we can calculate that the replacement of the glass fibers by carbon leads to the 33.2% more lifetime. 50% replacement leads to the 12.6% increased lifetime. 0.5% CNT nanoreinforcements (in fiber sizing) increase the lifetime by 16% (if the fibers are still from glass) or even 86% (if the fibers are replaced by carbon fibers). (All this for the dry conditions.) For the high humidity conditions, positive effects of the structural modifications are much stronger: 43% increased lifetime of the glass fibers are replaced by carbon (10%, if only 50% replaced), 24% increase if the glass composite is CNT nanoreinforced and 110% if both. If the carbon nanotubes in the fiber sizing are not randomly oriented but aligned, their positive effect increases by 16% additionally. Thus, one can state that the gains in the lifetime of the composites do justify some additional investments to produce the wind turbine blades from hybrid and nanoreinforced composites, with the investments in the range between 12 and 86% of the current costs. The justifiability of these investments becomes even more apparent when considering the blades which should work in off-shore conditions.

For comparison, Merugula and colleagues [24,25] demonstrated that the addition of 1–5 wt% of carbon nanofibers (CNF) to the interfaces of glass fiber reinforced epoxy composites for blades in 2 MW and 5 MW turbines leads to improved tensile stress and modulus, and allows 20% weight reduction of the blades, leading to the increased lifetime.

5. Conclusions

In this work, the potential of using hybrid and nanoreinforced composites for wind turbine and other long term cyclic, high humidity service conditions is analyzed, using computational experiments. Using 3D multiscale computational models of hybrid and nanoreinforced composites, we carry out systematic numerical experiments and determine the fatigue lifetime of composites with various structures under ideal dry conditions and expected off-shore service conditions (seawater humidity 65%). Having determined the local properties of the phases (carbon and glass fibers, CNT, epoxy, interface layers) under both dry and high humidity conditions from literature review, we introduced these data in our computational models and compared the fatigue performances of different composite structures.

Table 2
Proportionality and power coefficient of S–N curve of the considered model materials.

Case	Dry conditions			Humidity conditions		
	Pure glass reinforced composite (GRC)	Carbon RC	50/50 Glass/carbon hybrid	Glass RC	Carbon RC	50/50 Glass/carbon hybrid
$C, *10^{10}$	2.405	3.188	2.703	2.104	3.078	2.486
b	0.542	0.333	0.463	0.687	0.375	0.514
Case	Dry conditions, + CNT reinforcement			Humidity conditions, + CNT reinforcement		
	Glass RC	Carbon RC	50/50 Glass/carbon hybrid	Glass RC	Carbon RC	50/50 Glass/carbon hybrid
$C, *10^{10}$	2.804	4.455	3.704	2.588	4.386	3.533
b	0.486	0.318	0.408	0.557	0.338	0.446
Case	Dry conditions, 50/50 hybrid with CNT			Humidity conditions, 50/50 hybrid with CNT		
	Aligned CNTs in fiber sizing	Random CNTs in matrix		Aligned CNTs in fiber sizing	Random CNTs in matrix	
$C, *10^{10}$	4.313	3.163		4.128	2.92	
b	0.382	0.433		0.415	0.504	

The computational studies allowed to draw the following conclusions. Carbon reinforced composites have much better fatigue lifetime than glass reinforced composites (the 50/50 hybrids lie in between). The lifetime of composites depends strongly on the humidity conditions, and the glass fiber composites are most sensitive to humidity, while the carbon composites are least sensitive to it. The secondary CNT reinforcement ensures a much higher lifetime of composites, especially, when it is localized in the fiber sizing. The CNT reinforced glass fiber composites show lower humidity sensitivity than pure glass reinforced composites; yet, this effect is much weaker for carbon fiber composites. The CNT reinforcement in composites allows to reduce the sensitivity of the composite fatigue lifetime to the off-axis loading, also under high humidity conditions. The carbon fiber reinforced composites with CNT reinforcement is the fiber sizing have the best potential for use in the large wind turbine blades, especially, off shore turbines. Also, hybrid carbon/glass composites with the secondary CNT reinforcement have a high potential to replace the common composites, with sufficient improvement of the materials performances.

Acknowledgment

The author gratefully acknowledges the financial support of the Danish Council for Strategic Research (DSF) via the Sino-Danish collaborative project “High reliability of large wind turbines via computational micromechanics based enhancement of materials performances” (Ref. no. 10-094539). Furthermore, the author is grateful to the DSF for its support via the Danish Centre for Composite Structures and Materials for Wind Turbines (DCCSM) (Contract no. 09-067212).

References

- [1] Mishnaevsky Jr L, Brøndsted P, Nijsen R, Lekou D, Philippidis TP. Wind Energy 2012;15(1):83–97.
- [2] Ma PC, Zhang Y. Renew Sustain Energy Rev 2014;30:651–60.
- [3] Mishnaevsky Jr L, Zhou HW, Peng R, Dai G, Wang HW. Polymer nanocomposites for wind energy applications: perspectives and computational modeling. Proc Int Conf Nanomater Appl Prop 2013;2(4). 04NEA07 (4 p.).
- [4] Ong C-H, Tsai SW. The use of carbon fibers in wind turbine blade design: a SERI-8 blade example SAND2000-0478. Sandia National Laboratories contractor report. 2000.
- [5] Ashwill TD. Materials and innovations for large blade structures: research opportunities in wind energy technology. In: 50th AIAA structures, structural dynamics, & materials conference palm springs, May 2009; 2009.
- [6] Grande JA. Plast Technol 2008;54(10):68–75.
- [7] Haberkern H. Reinf Plast 2006;50(4):28–33.
- [8] Mishnaevsky Jr L, Dai GM. Compos Struct 2014;117:156–68.
- [9] Mishnaevsky Jr L, Dai GM. Comput Mater Sci 2014;81:630–40.
- [10] Dai GM, Mishnaevsky Jr L. Compos Sci Technol 2014;94:71–9.
- [11] Manders PW, Bader MG. J Mater Sci August 1981;16(8):2246–56.
- [12] Chiang MYM, Wang X, Schultheisz CR, He J. Compos Sci Technol 2005;65(11–12):1719–27.
- [13] Gutans J, Tamuzs V. Theor Appl Fract Mech 1987;7(3):193–200.
- [14] Bortolotti P. Carbon glass hybrid materials for wind turbine rotor blades [Master thesis]. Delft University of Technology; April 23, 2012.
- [15] Yao LN, Chou TW. Compos Struct 1989;12(1):27–37.
- [16] Summerscales J, Short D. Composites July 1978;9(3):157–66.
- [17] Sonparote PW, Lakkad SC. Fibre Sci Technol June 1982;16(4):309–12.
- [18] Diez-Pascual AM, Naffakh M, Marco C, Gomez-Fatou MA, Ellis GJ. Curr Opin Solid State Mater Sci 2014;18(2):62–80.
- [19] De Greef N, Gorbatikh L, Godara A, Mezzo L, Lomov SL, Verpoest I. Carbon 2011;49(14):4650–64.
- [20] Godara A, Gorbatikh L, Kalinka G, Warrier A, Rochez O, Mezzo L, et al. Compos Sci Technol 2010;70(9):1346–52.
- [21] Godara A, Mezzo L, Luizi F, Warrier A, Lomov SV, van Vuure AW, et al. Carbon 2009;47(12):2914–23.
- [22] Siddiqui N, Sham M, Tang B, Munir A, Kim J. Compos A 2009;1606–14.
- [23] Zhu J, Imam A, Crane A, Lozano K, Khabashesh VN, Barrera EV. Compos Sci Technol 2007;67(7–8):1509–17.
- [24] Merugula L, Khanna V, Bakshi BR. Environ Sci Technol 2012 Sep 4;46(17): 9785–92.
- [25] Merugula L, Khanna V, Bakshi BR. Comparative life cycle assessment: reinforcing wind turbine blades with carbon nanofibres. In: Sustainable systems and technology (ISSST), 2010 IEEE symposium on sustainable systems and technology, Washington, DC: May 17–19, 2010. p. 1–6.
- [26] Bekyarova E, Thostenson ET, Yu A, Itkis ME, Fakhrutdinov D, Chou T, et al. J Phys Chem C 2007;111:17865–71.
- [27] Bekyarova E, Thostenson ET, Yu A, Kim H, Gao J, Tang J, et al. Langmuir 2007;23(7):3970–4.
- [28] Wicks SS, Guzman de Villoria R, Wardle BL. Compos Sci Technol 2010;70(1): 20–8.
- [29] Dai GM, Mishnaevsky Jr L. Compos Sci Technol 2014;91:71–81.
- [30] Dai GM, Mishnaevsky Jr L. Compos Sci Technol 2013;74:67–77.
- [31] Mishnaevsky Jr L, Brøndsted P. Mater Sci Eng A 2008;498(1–2):81–6.
- [32] Li CY, Chou Tsu-Wei. Compos Part A 2009;40:1580–6.
- [33] Li CY, Chou Tsu-Wei. Compos Sci Technol 2008;68:3373–9.
- [34] Dai GM, Mishnaevsky Jr L. Comput Mater Sci. December 2014;95:684–92.
- [35] Mishnaevsky Jr L, Brøndsted P. Compos Sci Technol 2009;69(3–4):477–84.
- [36] Kushch VI, Shmegeva SV, Brøndsted P, Mishnaevsky Jr L. Int J Eng Sci 2011;49(1):17–29.
- [37] Peng RD, Zhou HW, Wang HW, Mishnaevsky Jr L. Comput Mater Sci 2012;60: 19–31.
- [38] Wang HW, Zhou HW, Peng RD, Mishnaevsky Jr L. Compos Sci Technol 2011;71(7):980–8.
- [39] Thostenson ET, Li WZ, Wang DZ, Ren ZF, Chou TW. J Appl Phys 2002;91: 6034–7.
- [40] Krueger R. Development of a benchmark example for delamination fatigue growth prediction. 2010. NASA/CR-2010-216723, NIA report no. 2010–04.
- [41] Rybicki EF, Kanninen MF. A finite element calculation of stress intensity factors by a modified crack closure integral. Eng Fract Mech 1977;9: 931–8.
- [42] Mishnaevsky Jr L, Lippmann N, Schmauder S. Int J Fract 2003;120:581–600.
- [43] Krueger R. Appl Mech Rev 2004;57:109–43.
- [44] Sanche-Portal D, Artacho E, Soler JM, Rubio A, Ordejón P. Phys Rev B 1999;59: 12678–88.
- [45] Yu MF, Files BF, Arepalli S, Ruoff RS. Phys Rev Lett 2000;84:5552–5.
- [46] Yu MF, Lourie O, Dyer MJ, Moloni K, Kelly TF, Ruoff RS. Science 2000;287: 637–40.
- [47] Joshi P, Upadhyay SH. Comput Mater Sci 2014;87:267–73.
- [48] Ghohi PP. J Reinf Plast Compos 2010;29:685–99.
- [49] Ray BC. J Colloid Interface Sci 2006;298:111–7.
- [50] Reeder JR. 3D mixed-mode delamination fracture criteria e an experimentalist's perspective. M/S 188E, Hampton, VA 23681–2199, USA: NASA Langley Research Center; 2006.
- [51] Liao WC, Sun CT. Compos Sci Technol 1996;56(4):489–99.
- [52] Reeder JR. A bilinear failure criterion for mixed-mode delamination. In: Campioneschi Jr , editor. Composite materials: testing and design, ASTM STP 2016. W. Conshohocken, PA: ASTM Int; 1993. p. 303–22.
- [53] Pinho ST, Robinson P, Iannucci L. Compos Sci Technol 2006;66:2069–79.
- [54] König M, Krüger R, Kussmaul K, Alberti MV, Gadke M. Characterizing static and fatigue interlaminar fracture behaviour of a first generation graphite/epoxy composite. In: Hooper SJ, editor. Composite materials: testing and design, ASTM STP 1242, 13th vol. American Society for Testing and Materials; 1997. p. 60–81.
- [55] Murri GB, Martin RH. Effect of initial delamination on mode I and mode II interlaminar fracture toughness and fatigue fracture threshold. Hampton, Virginia 23665: USA: NASA Langley Research Center, NASA-TM-104079; 1991.
- [56] Schwartz HS, Hartness JT. Effect of fiber coatings on interlaminar fracture toughness of composites. In: Toughened composites: symposium on toughened composites, issue 937. Baltimore, MD; 1987.
- [57] Singh S, Greenhalgh E. Delamination growth in epoxy-matrix composites under cyclic loading: implications for design and certification. In: 8th Europe conf compo materials (ECCM-8), Naples, Italy; June 1998.
- [58] O'Brien TK, Johnston WM, Toland GJ. Mode II interlaminar fracture toughness and fatigue characterization of a graphite epoxy composite material. Hampton, Virginia 23681–2199, USA: NASA Langley Research Center, NASA/TM-2010-216838; 2010.
- [59] Jose S, Kuma RK, Jana MK, Rao GV. Compos Sci Technol 2001;61:1115–22.
- [60] Valsson S, Bharat A. Impact of air temperature on relative humidity – a study. Archit-Time Space People 2011;38–41.
- [61] Hoon Lee Ji, Rhee Kyong Yop, Lee Joong Hee. Appl Surf Sci 1 October 2010;256(24):7658–67.
- [62] Rhee KY, Ha SR, Park SJ, Kim HJ, Jung DH. Mater Sci Eng A 2006;419:209–13.
- [63] Zafar A, Bertocco F, Schjødt-Thomsen J, Rauhe JC. Compos Sci Technol 2012;72:656–66.
- [64] Li Mei. Temperature and moisture effects on composite materials for wind turbine blades [PhD thesis]. Bozeman, Montana: Montana State University; 2000.
- [65] Chawla K. Composite materials: science and engineering. 3rd ed. Springer; 2012.
- [66] Buehler FU, Seferis JC. Compos Part A 2000;31(7):741–8.
- [67] Guedes RM, Sa A. J Reinf Plast Compos October 2010;29:3095–103.
- [68] van der Wal JS. Water resistance of glass fibre reinforced epoxy (GFRP) and carbon fibre reinforced epoxy (CFRP) composite. 2006. Diffusion-polymer-s.com, Netherlands.
- [69] Kinloch AJ. Structural adhesives: developments in resins and primers. Elsevier Applied Science Publishers; 1986.

- [70] Grant ST, Bradley LW. *J Compos Mater* 1995;29:853–67.
- [71] Jen Yi-Ming, Huang Chien-Yang. *Trans Can Soc Mech Eng* 2013;37(3).
- [72] Adams RD, Singh MM. *Compos Sci Technol* 1996;56(8):977–97.
- [73] Bretz PE, Hertzberg RW, Manson JA. *J Mater Sci* 1979;14:2482–92.
- [74] Armstrong JL, Matthewson MJ. *J Am Ceram Soc* 2000;83:3100–8.
- [75] Nishikawa Y, Okubo K, Fujii T. *JSME Int J* 2005;48:73–8.
- [76] Shan Y, Liao K. *Compos Part B Eng* 2001;32(4):355–63.
- [77] Shan Y, Lai KL, Wan KT, Liao K. *J Compos Mater* 2002;36(2):159–72.
- [78] Selzer R, Friedrich K. *Compos Part A* 1997;28A:595–604.
- [79] Jen YM, Huang Ch. Combined temperature and moisture effect on the strength of carbon nanotube reinforced epoxy materials. *Trans Can Soc Mech Eng, ICETI* 2012-J1082_SCI, no. 13-CSME-61, E.I.C. Accession 3519. <http://www.tcsme.org/Papers/Vol37/Vol37No3Paper47.pdf>.
- [80] Knoll JB, Riecken BT, Kosmann N, Chandrasekaran S, Schulte K, Fiedler B. *Composites Part A December* 2014;67:233–40.
- [81] Loos MR, Yang J, Feke DL, Manas-Zloczower I. *Polym Eng Sci* 2012;52:1882–7.
- [82] Zhang W, Picu RC, Koratkar N. *Appl Phys Lett* 2007;91:193109.
- [83] Zhang W, Picu RC, Koratkar N. *Nanotechnology* 2008;19:285709.
- [84] Mishnaevsky Jr L. *Compos Part B* 2015;68:75–84.
- [85] Thomsen OT. *J Sandw Struct Mater* 2009;11(1):7–26.
- [86] Manwell JF, McGowan JG, Rogers AL. Wind energy explained: theory, design and application.
- [87] Veldkamp D. Chances in wind energy. A probabilistic approach to wind turbine fatigue design [PhD thesis]. DUWIND Delft University Wind Energy Research Institute; 2006. 290 p.
- [88] Veers PS, Sutherland HJ, Ashwill TD. Fatigue life variability and reliability analysis of a wind turbine blade. Albuquerque, NM: Sandia National Labs.; 1991. 5 p.
- [89] Lange C. Probabilistic fatigue methodology and wind turbine reliability. UMI; 1996.